

Royal Mint,

PRETORIA.

13th February, 1933.

GOLD RECEIVED FOR EXAMINATION FROM PROFESSOR L. FOUCHE.

---

	Weight with adhering clay.	Fineness of gold.
Spiral necklace	.415 ounce troy.	91.23%
Fluted piece	.407 " "	93.82%
Concave "	.363 " "	91.59%
Beads in tube	.104 " "	Approx. fine gold.

The fluted and concave pieces are respectively 10/1000ths and 9/1000ths of an inch thick.

The percentages of gold given above were of necessity made by assaying a minute quantity of each piece and if it were possible to use an adequate sample the figures might vary to the extent of  $\pm .2\%$ .

R. PEARSON.

R. 305.

BC.

2.111.1933-50.