

REPORT ON GOLD CONTENT OF MATERIAL RECEIVED ON 10.3.33 FROM

Professor Foucho.

1. Weight of beaten gold in form of plates, Rhinoceros, etc.	12.34 oz. Tery.
2. Weight of beads	15.04 " "
3. Weight of Spiral Bands including 45.34 oz. and 2.48 oz. of lighter colour	<u>47.82</u> " "
TOTAL	<u>75.20</u> " "

Assay.

Fine Gold Content.

Plate	12.34 oz. --	944.5	11.65 oz. Tery.
Beads	15.04 --	911.0	13.70 " "
Spirals	45.34 --	945.0	42.64 " "
" (lighter colour)	2.48 --	894.0	<u>2.32</u> " "
Total fine gold			<u>70.41</u> " "

Total weight of fine gold @ £4.4s.11.45 d. per oz. = £299. 1s. 7d.

The above is a fair estimate of the value of fine gold contained in this material.

R. PEARSON.

DEPUTY MASTER.

Royal Mint,
Proctoria.
15.3.33.

R.331.

BC. 17.3.1933-45